

SPECIES CHARACTERISTICS

SELECT:

Wood will be selected for optimum color for the species selected. Color and grain matching will be done throughout the order, in order, to provide a more uniform look. Select material will exhibit fewer and smaller mineral streaks as well as pin knots, than standard grade. Ruck Cabinet Doors only offers select grade to ensure consistency and quality.

PAINT GRADE:

As our most economical material grade, this will typically include any natural characteristics commonly found in this species. Heartwood, sapwood, sound knots and other wood characteristics are considered acceptable and staves will not be color/grain matched.

GRADE CHARACTERISTICS

RUSTIC:

All naturally occurring characteristics of the wood selected are considered allowable. Knots may be a variety of sizes and may be both sound and unsound. Characteristics such as worm tracks/holes, ingrown bark and split/ open knots are considered acceptable and will not be puttied.

QUARTER SAWN:

Quarter sawn is achieved by cutting at a right angle to the circumference of the tree producing a flake-like or “ribboning” look on the face of the lumber.

RIFT SAWN:

Rift sawn is achieved by milling perpendicular to the log’s growth rings producing a linear grain pattern with no flecking. The lumber is very dimensionally stable and has a unique linear appearance.

FLAT PANEL:

All of our 5.2MM panels have an “A” grade face (unless otherwise determined by the material grade) with a super refined MDF core. This provides a much better product to finish and helps eliminate the rattle found in plywood core doors.

SPECIE & GRADE AVAILABILITY



EFFECTIVE JULY 1, 2019, RUCK CABINET DOORS WILL NO LONGER OFFER FACTORY OR STANDARD GRADE WOOD IN ANY SPECIES.

Grade Availability & Unfinished Lead-time

SPECIE	SELECT	PAINT GRADE	RUSTIC	QUARTER SAWN	RIFT SAWN
Alder	12 days		12 days	12 days	
Ash	12 days				
Birch	7 days				
Cherry	12 days		12 days		
European Beech	12 days				
Hickory	12 days		12 days		
Maple	7 days				
Mahogany	12 days				
Pine	12 days		12 days		
Poplar	7 days				
Red Oak	7 days		7 days	7 days	7 days
Walnut	12 days				
White Oak	12 days			12 days	12 days
MDF (Super Refined)*		7 days			

*REFER TO MDF TECHNICAL DATA SHEET FOR MORE PROPERTY INFORMATION